

TEHNIČKA GUMA



NAZIV	BOJA	SPEC. TEŽINA gr/cm ³	TVRDOĆA Shore A	ZAT. ČVRSTOĆA kg/cm ²	ISTEZANJE do %	TEMP. OTPORNOST °C
SBR standard	crna	1,5	65	60	250	-20 do +70
SBR armiran platnom	crna	1,15	65	60	250	-20 do +70
SBR + NR Antiabraziv L	crna	1,2	60	100	400	-30 do +70
NR 45 prirodna guma	crna	1,15	45	120	500	-40 do +70
NBR prehrambena	bijela	1,45	60	80	500	-30 do +90
NBR 70/ST - NITRIL	crna	1,4	70	80	300	-30 do +70
NBR 60 C - NITRIL	crna	1,6	60	40	250	-30 do +70
EPDM M65 C	crna	1,4	65	80	250	-40 do +100
EPDM M70 S	crna	1,3	70	100	350	-40 do +130
CR - NEOPREN 60 C	crna	1,3	60	60	250	-30 do +80
CR - NEOPREN 70 ST	crna	1,4	70	80	250	-30 do +90
CR - NEOPREN 60 S	crna	1,4	60	100	350	-30 do +110
VMQ-SILIKON	prozirna	1,2	60	85	300	-50 do +200
IIR-Butyl	crna	1,2	70	80	300	-40 do +160